



ARIA POLYMER NICKAN MEHR

Paraffin Wax 1-2%

Product Data Sheet

Characteristic	Result	Method	Specification
Oil Content	1-2%	ASTM D445	-
Congealing Point	57 °C	ASTM D938	-
Flash Point	220-245 °C	ASTM D92	-
Color (Lovibond)	White 0.1 Yellow	BP 2013 17 Method A 2" cell	White or almost White
Drop Melting Point	58-60 °C	ASTM D127	-
Odor	Odorless	BP 2013	Odorless
Specific Gravity at 25 °C	0.81-0.85 g/cm ³	ASTM D445	-

Packing:

Carton / PP Bags / Jumbo Bags

Application:

Candles, Match sticks, Tires, cosmetics, wooden boards, tarpaulin, etc.