



ARIA POLYMER NICKAN MEHR

Paraffin Wax 3-5%

Product Data Sheet

Characteristic	Result	Method
Color (Iovibond)	0.3Y-0.5Y	IP-17 Method A 2" cell
Congealing Point	63-68 (deg)	ASTM D938
Melting Point	59-64 C (deg)	ASTM D87
Oil Content (% wt)	3-5%	ASTM D721
Kinematic Viscosity @ 100 °C	6-7.5 Ccst	ASTM D445
Density @ 100 C (deg)	0.760-0.770 gr/cm ³	ASTM D1298
Flash Point	Min 250 C (deg)	ASTM D92
Form	Solid	-
Quality	Semi-refined	-

Packing:

Carton / PP Bags / Jumbo Bags

Application:

Candles, Match sticks, Tires, cosmetics, wooden boards, tarpaulin, etc.